

1 Disclaimer

2 'This is a copy of the accepted paper as submitted for publication. Readers are advised to
3 refer to the final version of the paper which can be found at

4
5 <https://pubs.acs.org/doi/10.1021/acs.est.8b05297>

6 **Are we speaking the same language? Recommendations for a definition and**
7 **categorization framework for plastic debris**

8
9 **Nanna B. Hartmann^{1,*}, Thorsten Hüffer^{2,*}, Richard Thompson³, Martin Hassellöv⁴, Anja**
10 **Verschoor⁵, Anders Egede Daugaard⁶, Sinja Rist¹, Therese Karlsson⁴, Nicole**
11 **Brennholt⁷, Matthew Cole⁸, Maria P. Herrling⁹, Maren Heß¹⁰, Natalia P. Ivleva¹¹, Amy L.**
12 **Lusher¹², Martin Wagner^{13,*}**

13 ¹ Technical University of Denmark, Department of Environmental Engineering,
14 Bygningstorvet B115, 2800 Kgs. Lyngby, Denmark

15 ² University of Vienna, Department of Environmental Geosciences; Environmental Science
16 Research Network; and Research Platform Plastics in the Environment and Society
17 (PLENTY), Althanstrasse 14, 1090 Vienna, Austria

18 ³ School of Biological and Marine Sciences, Plymouth University, Plymouth PL4 8AA, United
19 Kingdom

20 ⁴ University of Gothenburg, Department of Marine Sciences, Kristineberg 566, 45178
21 Fiskebäckskil, Sweden

22 ⁵ National Institute for Public Health and the Environment, Antonie van Leeuwenhoeklaan 9,
23 3721 MA Bilthoven, The Netherlands

24 ⁶ Technical University of Denmark, Department of Chemical and Biochemical Engineering,
25 Danish Polymer Centre, Søtofts Plads B227, 2800 Kgs. Lyngby, Denmark

⁷ Federal Institute of Hydrology, Department Biochemistry and Ecotoxicology, Am Mainzer
Tor 1, 56068 Koblenz, Germany

⁸ Marine Ecology & Biodiversity, Plymouth Marine Laboratory, Prospect Place, The Hoe,
Plymouth PL1 3DH, United Kingdom

⁹ Ovivo Switzerland AG, Hauptstrasse 192, 4147 Aesch, Switzerland

¹⁰ North Rhine Westphalia State Agency for Nature, Environment and Consumer Protection,
Department Water Management, Water Protection, Postfach 101052, 45610
Recklinghausen, Germany

¹¹ Technical University of Munich, Institute of Hydrochemistry, Chair of Analytical Chemistry
and Water Chemistry, Marchioninstr. 17, 81377 Munich, Germany

¹² Norwegian Institute for Water Research (NIVA), 0349 Oslo, Norway

¹³ Norwegian University of Science and Technology (NTNU), Department of Biology, 7491
Trondheim, Norway

* Corresponding authors: nibh@env.dtu.dk, thorsten.hueffer@univie.ac.at,
martin.wagner@ntnu.no

Keywords: harmonization, legislation, litter, microplastics, plastics, terminology

Synopsis

Plastic pollution is a global issue. However, there is no consensus on how to define and
categorize plastic debris, for instance in terms of materials or size classes. As this ambiguity
creates miscommunication, we propose a framework to define plastic debris based on

48 material properties and categorize it according to size, shape, color, and origin. This should
49 help to clarify what we actually mean when we talk about plastic debris.

50 **Abstract**

51 The accumulation of plastic litter in natural environments is a global issue. Concerns over
52 potential negative impacts on the economy, wildlife, and human health provide strong
53 incentives for improving the sustainable use of plastics. Despite the many voices raised on
54 the issue, we lack a consensus on how to define and categorize plastic debris. This is
55 evident for microplastics, where inconsistent size classes are used, and where the materials
56 to be included are under debate. While this is inherent in an emerging research field, an
57 ambiguous terminology results in confusion and miscommunication that may compromise
58 progress in research and mitigation measures.

59 Therefore, we need to be explicit on what exactly we consider plastic debris. Thus, we
60 critically discuss the advantages and disadvantages of a unified terminology, propose a
61 definition and categorization framework and highlight areas of uncertainty.

62 Going beyond size classes, our framework includes physico-chemical properties (polymer
63 composition, solid state, solubility) as defining criteria and size, shape, color, and origin as
64 classifiers for categorization. Acknowledging the rapid evolution of our knowledge on plastic
65 pollution, our framework will promote consensus-building within the scientific and regulatory
66 community based on a solid scientific foundation.

1 Introduction

Plastic pollution is a substantial environmental problem. Plastic debris, that is, plastic items occurring in natural environments without fulfilling an intended function, is persistent, mobile, and ubiquitous in terrestrial and aquatic environments, including urban, rural, and remote locations. Large plastic litter is readily visible and adversely affects wildlife species through entanglement, ingestion and lacerations.¹ Microscopic plastic debris (i.e., microplastics) has, until recently, largely been an overlooked part of plastic pollution. This has changed in the last decade, over which time growing scientific, public, and political interest has focused on the smaller size fractions, in particular those in the micrometer size range.² Today, research into the formation, features, further fragmentation, chemical interactions, environmental fate, and potential impacts of microplastics is increasingly abundant.³

The term 'microlitter' was used in 2003 to describe the fine fraction of marine plastic litter with sizes of 63–500 μm .³ Similarly, mesolitter, macrolitter, and megalitter were defined as having sizes of <5 to 10 mm, <10 to 15 cm or measuring decimeters or more across, respectively.⁴ In 2004, the term 'microplastics' was popularized to describe truly microscopic plastic fragments with typical diameters down to $\sim 20 \mu\text{m}$.⁵ While this paper described the accumulation of microplastics in the seas around the United Kingdom, it did not define them. In 2008, experts attending a meeting hosted by NOAA proposed a working definition in which microplastics are all plastic particles <5 mm in diameter,⁶ which has become the most frequently used definition. Although not yet detected in environmental samples, sub-micron sized particles are expected to form in the environment through fragmentation of larger plastics.^{7, 8} These have been termed nanoplastics.^{9, 10} Due to the evolving research on plastic debris, a certain nomenclature has developed. Nonetheless, the terminology remains ambiguous and conflicting, for instance regarding the size classes (Figure 1). So far, "[t]here is no internationally agreed definition of the size below which a small piece of plastic should be called a microplastic".¹¹

In the context of this paper, categorization refers to a systematic division of plastic debris into groups according to pre-established criteria. Hereby, plastic objects are grouped based on similarity. A commonly used categorization system is based on size using the prefixes of mega-, macro-, meso-, micro-, and nano. In addition, plastic debris can also be categorized based on their origin, shape, and polymer type.¹² However, a systematic framework for categorizing plastic debris is currently missing.

While most of the discourse on what makes a plastic item, for instance, a “microplastic” focuses on size as only criterion,¹³ we first need to revisit the question of what plastics actually are. This is important because – apart from the commodity polymers – there is no consensus on which materials to include in the term ‘plastics’. For instance, some studies consider cellophane, i.e., regenerated cellulose, as plastics^{14, 15} while it can be argued that it is not. In addition, definition criteria from polymer sciences are not stringently applicable to plastic debris. For instance, rubber is not plastic according to some polymer chemistry definitions.¹⁶ Yet, environmental researchers consider rubber-containing tire wear a major component of microplastic pollution.^{17, 18} The same is true for paint particles. To clarify, we discuss basic physico-chemical properties as ‘definition criteria’ before considering size, shape, color, and origin as ‘classification criteria’ for the categorization of plastic debris.

2 Do we need a common terminology?

The lack of consensus on a definition and categorization of plastic debris results in an ambiguous communication and the generation of incomparable data. While this situation inevitably calls for a harmonization, we need to keep in mind the implications of such a framework. Categorizing plastic debris into different classes (e.g., sizes) implicitly suggests that the items within one category have some ‘likeness’ whereas plastics in different categories are somehow different. This may be perceived as similarity in hazardous properties or environmental behavior. Such connotation has emerged for the term microplastics, using size as a key feature, already.¹⁹ On the downside, this may point research towards properties that are irrelevant and result in neglecting features that are potentially important. A framework can, thus, shape the research field and affect current and future mitigation measures based on how it frames the problem. This will also affect the risk perception and the hypotheses generated to examine it.²⁰

In the area of engineered nanomaterials, the process of agreeing on a common terminology has been ongoing for more than a decade and is under continuous debate^{21, 22} and revision.²³ For nanomaterials, the European Commission ‘Recommendation on a Definition of Nanomaterials’ states that: *“an upper limit of 100 nm is commonly used by general consensus, but there is no scientific evidence to support the appropriateness of this value.”*²⁴ It has been further specified that *“clear [size] boundaries were primarily introduced with the regulatory purpose of the definition in mind rather than for scientific reasons.”*²³ Hence, the size boundaries are not scientifically justified but rather based on pragmatic reasons and general consensus. As behavior and toxicity will also depend on properties other than size, a purely scientific definition of nanomaterials may never be achieved – at least not if it shall have any practical value.

For plastic debris, similar considerations do apply: There is no clear scientific justification for the currently applied size boundaries. The 5 mm upper limit for microplastics proposed by NOAA⁶ is somewhat biologically informed as particles of this size were considered more

137 likely to be ingested compared to larger items. Still, the decision on size limits is not based
138 on actual evidence but rather on pragmatism.¹¹

139 Ultimately, the question whether to establish a definition/categorization framework for plastic
140 debris is at the heart of two conflicting points of view. On the one hand, there is the notion to
141 refute any attempt to unify the terminology as this restricts scientific freedom and narrows
142 down the scientific focus to what is included in the definition. On the other hand, there is the
143 view that a globally accepted definition is an essential prerequisite to tackle the issue,
144 especially from a regulatory perspective.²⁵ As environmental scientists, we work in the space
145 between these poles and can neither ignore the importance of academic freedom nor our
146 obligation to support science-based policy-making. While we acknowledge that a flexible,
147 adaptive, and continuously updated framework would be ideal for science, we recognize that
148 this conflicts with regulatory needs and processes. For instance, the control of microplastic
149 emissions will depend on a common definition. Accordingly, the discourse needs to focus on
150 developing a pragmatic and workable framework enabling effective regulation while not
151 restraining scientific freedom.

3 Guiding principles for formulating a definition/categorization framework

When developing a framework for defining and categorizing plastic debris, we considered the following guiding principles, assumptions and disclaimers:

- 1) A definition/categorization framework should not be tied to current methodological and analytical capabilities as these evolve constantly.
- 2) A definition/categorization framework should not be limited to size as sole criterion as properties other than size contribute to the impacts of plastic debris.
- 3) A definition can be based on scientific criteria using the physical and chemical properties of the materials included as plastics.
- 4) A categorization cannot be purely science-based because the biologically relevant properties needed to categorize plastic objects are not well understood.
- 5) Accordingly, any categorization will, to some extent, be arbitrary and must be based on conventions formed by consensus and guided by pragmatism.
- 6) Thus, the proposed definition/categorization framework is a recommendation that aims at promoting consensus-building on a common terminology.
- 7) Consensus-building in academia is a dynamic process rather than a one-time decision. Thus, the proposed framework must be subjected to criticism and revision.
- 8) Regardless of the existence of this or any other definition/categorization framework, scientific data should always be reported in the most comprehensive way, that is, in accordance with the latest state of the science.
- 9) A material should not be excluded from the framework based on its degradability or state of degradation as even “degradable” materials will form smaller fragments before they mineralize.
- 10) The main audience of this framework are researchers, as a common terminology needs to form in the community producing the primary knowledge on plastic pollution. However, the framework can also serve as point of departure for policy-makers and the regulatory community.

4 Recommendation of a definition/categorization framework for plastic debris

To structure the discussion on what plastic debris is, we propose a framework which differentiates between defining criteria that address basic properties and auxiliary criteria for categorizing plastic debris (principle 3 and 4, Figure 2). According to Merriam-Webster's dictionary, a definition is "*a statement expressing the essential nature of something.*" A good question to ask about any definition is therefore: does it actually capture the property that we are trying to define? For plastic debris, we consider the following as relevant defining properties: chemical composition, solid state, and solubility (criteria I-III). These will determine whether a material classifies as 'plastic' and, thus, 'plastic debris' when found in natural environments. For further categorization, we discuss size, shape and structure, color, and origin (criteria IV-VII).

4.1 Criterion I: Chemical composition

The chemical composition is the most fundamental criterion for defining plastic debris. Some disagreement exists on which polymers should be considered 'plastics'. For instance, according to ISO plastic is a "*material which contains as an essential ingredient a high molecular weight polymer and which, at some stage in its processing into finished products, can be shaped by flow.*"¹⁶ In contrast to thermoplastics and thermosets, some elastomers (e.g., rubbers) are excluded from this definition. This mirrors the industrial landscape and, thus, has historic rather than scientific reasons. Questions, therefore, arise whether materials derived from rubber or inorganic/hybrid polymers (e.g., silicone) qualify as plastics. Also, are plastics with a high content of low-molecular weight additives (e.g., polyvinyl chloride (PVC) containing >50% plasticizers) included? And should polymer composites fall under such a definition? Finally, should crystalline fibers, which are not shaped by flow, be excluded from a definition even though they are composed of the same polymers as other plastic debris? These questions reflect the different perspectives of material and environmental sciences.

a. Polymers

As the ISO definition of plastics excludes certain materials, which are relevant in environmental terms (e.g., elastomers), we use a broader definition as point of departure. IUPAC defines a polymer as a “*molecule of high relative molecular mass, the structure of which essentially comprises the multiple repetition of units derived, actually or conceptually, from molecules of low relative molecular mass.*”²⁶ Typically, polymers have a molecular mass of $>10,000 \text{ g mol}^{-1}$.²⁷

As a next level, we can use the origin of the polymer as criterion and differentiate between natural and artificial (man-made, synthetic) polymers. With regard to the former, there is agreement that natural polymers (e.g., DNA, proteins, wool, silk, cellulose) are not plastics while synthetic polymers commonly are. Modified natural polymers, natural rubber and cellulose further processed to make the final polymer (rayon and cellophane) for instance, represent a special case. Because these polymers are heavily modified, they can also be considered artificial and should be included in a definition of plastic debris.

The inclusion of natural polymers that have been slightly processed (e.g., dyed wool) is more difficult. This predominantly concerns polymer fibers used for textiles and we do not have sufficient information to benchmark the occurrence and impacts of natural, modified natural, and synthetic fibers, respectively. However, because their essential ingredient is a natural polymer, we propose to exclude slightly modified natural fibers from a definition.²⁸

Conventional plastics are petroleum-based and include the commodity plastics polyethylene (PE), polypropylene (PP), polyurethane, polyethylene terephthalate (PET), polystyrene (PS), and PVC. Recently, bio-based plastics synthesized from non-fossil feedstock have entered the market. Bio-based monomers can be used to make the conventional polymers (e.g., bio-PET, bio-PE) or biodegradable polymers such as polylactic acid and polyhydroxyalkanoates.²⁹ A third type of plastics is mainly produced from inorganic monomers. These inorganic or hybrid polymers – silicone is the most prominent example – are usually excluded from plastics definitions, since they are elastomers. However, because all three polymer classes are synthetic and are emitted to the environment, we recommend including them in a definition of plastic debris.

b. Additives

Plastics can contain a broad range of low molecular weight additives to improve their processability, properties, and performance. They are, thus, an essential part of the formulation. The major classes of additives include plasticizers, stabilizers, flame retardants, flow modifiers, processing aids, impact modifiers, and antioxidants.^{30, 31} In addition, pigments, biocides, and fragrances can be added. Additives and other small molecules present in plastics (e.g., monomer residues or by-products formed during production) may be toxicologically relevant when leaching from the material. Nonetheless, they are not of specific importance for a definition because the polymer backbone, not its additive content, defines a plastic material. Polymers containing high amounts of additives (e.g., PVC) represent a special case. According to REACH,³² substances with an additive content of >50% are not polymers. In contrast, we propose to exclude the additive content as criterion because it will change continuously after the release into the environment.

c. Copolymers

Some synthetic polymers are produced “*from more than one species of monomer.*”²⁶ These include copolymers of acrylonitrile-butadiene-styrene (ABS), ethylene-vinyl acetate (EVA), and styrene-butadiene rubber (SBR). ABS and EVA are thermoplastic polymers (i.e., ‘plastics’ according to ISO) and, thus, can be considered plastic debris when found in the environment. The same argument can be applied to thermoplastic elastomers, such as styrenic block copolymers, thermoplastic olefins, and thermoplastic polyurethanes, which are widely used in automotive manufacturing. In line with the arguments made above, SBR (also an elastomer) and other synthetic rubber copolymers should be included in a definition.

d. Composites

Polymer composites consist of at least two components; the polymer matrix and (non)polymeric reinforcement. Classical thermoset composites include glass fiber-reinforced polyester or graphite reinforced epoxy, both used for instance for boat hulls. This also includes thermoplastics filled with various inorganic materials to reduce costs or improve

properties. Likewise, polyester textiles are often mixed with cotton or wool. We recommend including composites into a definition of plastic debris because synthetic polymers are an essential ingredient. However, it remains unknown whether setting a minimum polymer content of a material to qualify as plastics is appropriate and feasible.

Special cases 1: Surface coatings

One special case of composites are paint particles found in the environment. Surface coatings (such as paints) are applied as a thin layer to a surface for aesthetic or protective reasons.³³ Coatings are formulated, multi-component systems consisting of binders, pigments, fillers and extenders, solvents, and additives. Polymers are used as film formers and include (modified) natural resins, curing coating systems (e.g., polyester, alkyds, epoxy resin, urethane resins), and physically drying systems (acryl and vinyl (co)polymers).³³

The central question for including coating particles in a definition is whether the synthetic polymers used in surface coatings are considered plastics. Recent government reports argue that they should.^{34, 35} Indeed, particles originating from dried paints and lacquers containing cured thermosets can be considered plastic debris. Examples are coatings based on polyesters, vinyl esters, polyurethanes as well as epoxy, phenolic, acrylic resins and alkyd.³⁴ Accordingly, particles derived from paints and surface coatings containing synthetic polymers as an essential ingredient should be included in a definition. However, as in the case of composites, setting a threshold for a minimal polymer content is currently not possible.

Special case 2: Tire wear particles

Driving vehicles releases particles due to the abrasion of tires, termed tire wear particles (TWP). Some agencies have considered TWP to be 'microplastics'^{34, 36-38} because tires usually contain 40–60% of synthetic polymers (e.g., SBR or polybutadiene rubber). The exact composition of tires depends on their application.¹⁸ To classify TWP as plastic debris, two questions need to be addressed: First, are rubbers plastics? Here, we argue that they should be covered by the proposed definition (see criterion Ic). Second, do we need to take into account a changing chemical and material composition during weathering? As an

example, TWP will aggregate with road particles and form tire wear and road particles (TWRP) with a lower total polymer content. We argue it is not feasible to determine the polymer content of TWRP as this would need to happen for each individual particle. This is also true for other plastic particles forming heteroaggregates with other particulate matter. Accordingly, we propose to refer to the original material and to include TWP/TWRP in the definition because synthetic polymers are an essential ingredient of tires.

4.2 Criterion II: Solid state

While it might be common sense that plastics are solid materials, some polymers can be wax-like, semi-solid or liquid. According to the Global Harmonized System for Classification and Labelling of Chemicals (GHS) a solid substance or mixture “*does not meet the definitions of liquid or gas.*” As most polymers have a vapor pressure of <300 kPa (at 50 °C) and an initial melting point of >20 °C (T_m at 101.3 kPa) they are solid.³⁹ For most materials, the T_m determines the difference between the solid and the liquid state. However, amorphous and semi-crystalline plastics will behave differently when heated. Amorphous polymers (e.g., polymethyl methacrylate, ABS, PS) are hard, brittle materials below their glass transition temperature (T_g), whereas they become viscous and free flowing above. Semi-crystalline polymers (e.g., polyamide, polycarbonate, PE, PET, PP, PVC) have both, a T_g as well as a T_m . These polymers will be hard and brittle below their T_g but ductile, soft, and form stable below their T_m , and liquid above.

Plastics are used both as hard and brittle as well as softer and more ductile materials (plasticized PVC, PE, PP) and depending on molecular weight exist as waxy, semi-solids over a broad temperature range. For some polymers (e.g., rubber, PE, PP, PVC), T_g is relatively low. Accordingly, they are soft solids at ambient temperatures. Nevertheless, semi-crystalline polymers have a T_m high enough to classify them as solid according to GHS and can be included in a definition of plastic debris.

In contrast, amorphous polymers lack a specific T_m . Therefore, we propose to consider the T_g as a defining value. Accordingly, amorphous polymers with a $T_g > 20\text{ °C}$ should be included in a definition. Here, the properties of the bulk materials should be considered. However, the question remains whether wax-like polymers with a $T_g < 20\text{ °C}$ should be included as well. In this regard, the combination with other physico-chemical properties, such as viscosity, modulus of elasticity or tension at constant elongation, might be helpful.

Special case 3: Polymer gels

Polymer gels are often perceived as liquid rather than solid, due to their high liquid content and their soft and flexible appearance. However, in macromolecular science a gel is indeed “a solid composed of at least two components, one of which (polymer) forms a three-dimensional network [...] in the medium of the other component (liquid).”⁴⁰ Polymer gels come from a natural (e.g., gelatin, agarose) or synthetic feedstock (polyacrylamide, polyvinyl alcohol (PVA), low molecular weight polyethylene glycol (PEG)) and are used in a wide variety of applications. For instance, polyacrylamide copolymers are used as flocculation agents during wastewater treatment. While these gels are “solid” from a chemical perspective, they will become soft and viscous in water. Although this does not make them benign *per se* (we simply do not know), we argue that polymer gels are not particulate matter once in aquatic environments and should, therefore, be excluded from a definition and treated as an independent category of environmental polymers.

4.3 Criterion III: Solubility

Another important aspect is the polymer’s solubility. Most conventional polymers are poorly soluble in water, but some synthetic polymers readily dissolve in water (e.g., PVA or low molecular weight PEG). We propose using solubility as a criterion to define plastic debris and apply the REACH guidance provided by ECHA. Here, a substance is considered poorly soluble if their water solubility is $< 1\text{ mg L}^{-1}$ at 20 °C .⁴¹ Polymers that are poorly soluble according to REACH should be included in a definition of plastic debris.

341

342 **4.4 Criterion IV: Size**

343 Size is the criterion most frequently used to categorize plastic debris, with size classes
344 typically attributed with the nomenclature of nano-, micro-, meso-, and macroplastics. Particle
345 size will be of major ecological relevance because it is one important factor determining the
346 item's interaction with biota and its environmental fate.⁴²⁻⁴⁴ Currently, there is no clear
347 consensus on the use of size categories (Figure 1). Often, size limits are operationally
348 defined by the sampling method. As an example, some authors set the lower size limit of
349 microplastics to 333 μm because a 333 μm mesh plankton net is used for sampling.⁶

350 From a nomenclature point of view, it is intuitive to categorize the plastics based on the
351 conventional units of size. Accordingly, plastics with sizes in the nanometer scale (1–1,000
352 nm) should be nanoplastics. Following this reasoning and using the SI prefixes for length,
353 microplastics would have sizes of 1–1,000 μm , followed by milliplastics (1–10 mm),
354 centiplastics (1–10 cm), deciplastics (1–10 dm). This, however, conflicts with the current
355 terminology. For example, nanoplastics and microplastics are typically considered to be 1–
356 100 nm and 1–5,000 μm in size, respectively.⁴⁵ Accordingly, new size categories, fully
357 consistent with the SI nomenclature, would have little chance of being adopted by the
358 scientific community. As a pragmatic compromise, we propose the following categories:

- 359 - Nanoplastics: 1 to <1,000 nm,*
- 360 - Microplastics: 1 to <1,000 μm ,
- 361 - Mesoplastics: 1 to <10 mm,
- 362 - Macroplastics: 1 cm and larger.

363 *To conform to existing definitions of nanomaterials, a sub-division in nanoplastics (1 to <100
364 nm) and submicron-plastics (100 to <1,000 nm) can be made.

365 Another important question relates to the dimensions of the plastic item. Is it sufficient that it
366 possesses the given size in one, two or three dimensions to fall into one of the categories?

Current size classes for microplastics refer to the largest dimension of the item. This is straightforward for relatively spherical particles but more ambiguous for irregular particles and fibers.⁴⁵ For example, should a fiber with a diameter (i.e., two dimensions) of 500 μm and a length (i.e., one dimension) of 20 mm be classified as microplastic or macroplastic? If two dimensions in the micrometer range would be sufficient to qualify as a microplastic, this would theoretically imply that a thin thread of infinite length would still be a microplastic. This would correspond to the current practice of determining size by filtration through a net of a certain mesh size or by microscopy, whereby two dimensions are considered. However, a classification should not be based on current practices, which may change as the methodology advances. We, therefore, propose to use the largest dimension as classifier for the size category. The rationale behind this is that the largest dimension of an item will mainly determine the ingestion by biota. For fibers, we do recognize that the diameter may be more relevant and suggest that the dimensions used for categorization should then be defined in the specific study.

4.5 Criterion V: Shape and structure

Aside from size, plastic debris is commonly categorized based on shape, structure, and color. Frequent descriptors of shape are: spheres, beads, pellets, foams, fibers, fragments, films, and flakes.⁴⁶⁻⁴⁹ These are worth revisiting in order to apply a more stringent classification. The first three (spheres, pellets, beads) are often used synonymously. Additionally, the terms 'beads' and 'pellets' hints towards the origin of the particles, such as microbeads in cosmetics and pre-production pellets used for plastic manufacturing. If the origin of the specific particle can indeed be elucidated this would be an appropriate terminology. However, as this is often challenging it is instead beneficial to adopt more neutral descriptors, such as 'spheres' for particles with every point on its surface having the same distance from its center. The terms 'spheroids' and 'cylindrical pellets' can be used for approximate spheres and cylindrical shapes, respectively.

'Fragments' also represent a rather ambiguous category. It is commonly adopted to describe particles with irregular shape. The term, however, implies that these have been formed by fragmentation in the environment, which is not necessarily the case. For instance, irregular abrasives used in cosmetics are produced as such⁵⁰⁻⁵² and cannot be distinguished from particles generated by secondary fragmentation. While the category 'fragment' is likely to persist in the literature, an alternative and more accurate term is 'irregular particles'.

The category of 'films' is rather straight-forward as this includes planar objects which are considerably smaller in one dimension than in the other two. It is useful to classify films separately and it is often feasible to make that distinction for items >300 µm. Smaller objects tend to overlap and, due to practical constraints, may be pooled with 'irregular particles'.

Plastics that are significantly longer in one than wide in two dimensions (length-to-diameter ratio) are commonly (and interchangeably) described as fibers or filaments, with both terms describing thread-like structures. Within toxicology there is a long-standing tradition of referring to such structures as fibers rather than filaments.

For some types of fibers, their aspect ratio has been found to determine toxicological responses, for example in the case of asbestos and carbon nanotubes. Hence, from a toxicological perspective it makes sense to distinguish between different shapes of plastic debris using the neutral terminology described above. Additional information on the structure (e.g., material porosity) can be included when relevant and only when it can be established with certainty. For example, the descriptor 'foams' can draw unwanted parallels to styrofoam even though several plastic types can be visually similar. A more neutral descriptor for this type of porous materials would be 'expanded cellular plastics'.

4.6 Criterion VI: Color

Categorizing plastic debris according to color is useful to identify potential sources as well as potential contaminations during sample preparation. As with shape, the color of an object cannot easily be used to deduce the origin. Importantly, color information can be biased as

brighter colors are spotted more easily during visual inspection. In contrast, dark, transparent or translucent particles may be underrepresented. In addition, discoloration can take place during weathering as well as sample preparation, which should be considered in data reporting and interpretation. While we do not find color to be crucial in a categorization framework, it can make sense to include color as an additional descriptor. This can be the case in a biological context, where depending on an organism's feeding preferences, some colored plastic objects may be more or less likely to be mistaken as food.⁵³ As attributing colors may be subjective, the use of a standardized color palette, such as the Pantone Color Matching System, is preferable.

4.7 Optional criterion VII: Origin

The origin of plastic debris is commonly used as a classifier, especially for microplastics, which are categorized in 'primary' and 'secondary' microplastics. In the predominant view, 'primary' refers to microplastics intentionally produced in that size range whereas 'secondary' microplastics are formed in the environment through fragmentation or through wear and tear of plastic-containing items, such as TWP and fibers released from textiles during use.¹¹ An alternative perspective is that 'primary' also includes microplastics that are inherent by-products of the use of a product ("primary sources"),^{35, 37} such as TWP. In that view, secondary microplastics would originate from fragmentation during weathering, only. Since it is challenging, if not impossible, to determine whether a particle has been generated by fragmentation during intentional use or in the environment, we prefer to use the former classification.

From a regulatory point of view, it is relevant to distinguish between primary and secondary origin. This has consequences for risk management^{25, 54} as it may enable assigning responsibilities and apply the polluter pays principle. However, from a biological perspective, it does not matter if the plastic object encountered by an organism is intentionally manufactured. In addition, while primary microplastics tend to be more uniform and

448 homogenous (e.g., microbeads), this is not always the case.⁵⁰ A subsequent weathering will
449 further change the appearance, rendering a clear-cut distinction between primary and
450 secondary (micro)plastics often infeasible. Because of this ambiguity, we suggest not to use
451 'origin' to categorize plastics unless the primary origin of plastic debris can be established
452 convincingly. One such case is the detection of microbeads originating from ion exchange
453 resins from a specific production site.⁵⁵

5 Moving towards a workable terminology for plastic debris

The research on plastics in the environment is still in its infancy. This makes it an exciting and dynamic field but inevitably entails a certain scientific immaturity with regards to the hypotheses, concepts, and methods applied. This is also true in terms of the terminology we use. To promote consensus-building, we provide a framework for defining and further categorizing 'plastic debris'. We identify three defining criteria and four classifiers that can be used in such a framework. Based on this, we propose to define 'plastic debris' as objects consisting of synthetic or heavily modified natural polymers as an essential ingredient (criterion I) that, when present in natural environments without fulfilling an intended function, are solid (II) and insoluble (III) at 20 °C. We further recommend using the criteria size (IV), shape (V), color (VI), and origin (VII) to further categorize plastic debris (Table 1, Figure 2). Each criterion covers aspects on which consensus is likely as well as elements which are more debatable. Accordingly, the content of the framework cannot be fixed but may be revised as the field evolves. Thus, we welcome critical input by the readers and encourage a broader debate of this matter in the scientific community.

469 **Author contributions.** NBH, MW, and TH conceived and wrote the manuscript and
470 produced the figures. All co-authors critically discussed the ideas and concepts presented in,
471 commented on and reviewed the manuscript. All authors commit to organize and support the
472 post-publication consultation.

473 **Acknowledgments.** The German Water Chemistry Society supports the expert group
474 “Plastics in the aquatic environment,” whose members (TH, NB, MPH, MH, NI, MW) co-
475 authored the manuscript. MW has received funding from the European Union's Horizon 2020
476 Research and Innovation Programme under the Marie Skłodowska-Curie grant agreement
477 No 660306, from the German Federal Ministry for Transportation and Digital Infrastructure,
478 and the German Federal Ministry for Education and Research (02WRS1378, 01UU1603,
479 03F0789D).

References

1. Kühn, S.; Bravo Rebolledo, E. L.; van Franeker, J. A., Deleterious effects of litter on marine life. In *Marine Anthropogenic Litter*, Bergmann, M.; Gutow, L.; Klages, M., Eds. 2015; pp 75-116.
2. Sedlak, D., Three lessons for the microplastics voyage. *Environ Sci Technol* **2017**, *51*, (14), 7747-7748.
3. Blettler, M. C. M.; Abrial, E.; Khan, F. R.; Sivri, N.; Espinola, L. A., Freshwater plastic pollution: Recognizing research biases and identifying knowledge gaps. *Water Res* **2018**.
4. Gregory, M. R.; Andrady, A. L., Plastics in the marine environment. In *Plastics and the Environment*, Andrady, A. L., Ed. John Wiley & Sons, Inc.: Hoboken, 2003.
5. Thompson, R. C.; Olsen, Y.; Mitchell, R. P.; Davis, A.; Rowland, S. J.; John, A. W. G.; McGonigle, D.; Russell, A. E., Lost at sea: Where is all the plastic? *Science* **2004**, *304*, (5672), 838-838.
6. Arthur, C.; Baker, J.; Bamford, H. *Proceedings of the international research workshop on the occurrence, effects and fate of microplastic marine debris. Sept 9-11, 2008.*; National Oceanic and Atmospheric Administration: 2009.
7. Koelmans, A. A.; Besseling, E.; Shim, W. J., Nanoplastics in the aquatic environment. Critical review. In *Marine Anthropogenic Litter*, Bergmann, M.; Gutow, L.; Klages, M., Eds. 2015; pp 325-340.
8. Andrady, A. L., Microplastics in the marine environment. *Mar Pollut Bull* **2011**, *62*, (8), 1596-605.
9. Lambert, S.; Wagner, M., Characterisation of nanoplastics during the degradation of polystyrene. *Chemosphere* **2016**, *145*, 265-8.
10. Gigault, J.; Halle, A. T.; Baudrimont, M.; Pascal, P. Y.; Gauffre, F.; Phi, T. L.; El Hadri, H.; Grassl, B.; Reynaud, S., Current opinion: What is a nanoplastic? *Environ Pollut* **2018**, *235*, 1030-1034.

11. GESAMP *Sources, fate and effects of microplastics in the marine environment: a global assessment*; IMO/FAO/UNESCO-IOC/UNIDO/WMO/IAEA/UN/ UNEP/UNDP Joint Group of Experts on the Scientific Aspects of Marine Environmental Protection: 2015.
12. Verschoor, A. J. *Towards a definition of microplastics - Considerations for the specification of physico-chemical properties*; National Institute for Public Health and the Environment: 2015; p 41.
13. Frias, J. P. G. L.; Nash, R., Microplastics: Finding a consensus on the definition. *Mar Pollut Bull* **2019**, *138*, 145-147.
14. Yang, D.; Shi, H.; Li, L.; Li, J.; Jabeen, K.; Kolandhasamy, P., Microplastic pollution in table salts from China. *Environ Sci Technol* **2015**, *49*, (22), 13622-7.
15. Su, L.; Xue, Y.; Li, L.; Yang, D.; Kolandhasamy, P.; Li, D.; Shi, H., Microplastics in Taihu Lake, China. *Environ Pollut* **2016**, *216*, 711-719.
16. International Organization for Standardization Plastics - Vocabulary (ISO 472:2013). <https://www.iso.org/obp/ui/#iso:std:iso:472:ed-4:v1:en> (16.09.2018),
17. Kole, P. J.; Lohr, A. J.; Van Belleghem, F.; Ragas, A. M. J., Wear and tear of tyres: A stealthy source of microplastics in the environment. *Int J Environ Res Public Health* **2017**, *14*, (10).
18. Wagner, S.; Huffer, T.; Klockner, P.; Wehrhahn, M.; Hofmann, T.; Reemtsma, T., Tire wear particles in the aquatic environment - A review on generation, analysis, occurrence, fate and effects. *Water Res* **2018**, *139*, 83-100.
19. Kramm, J.; Volker, C.; Wagner, M., Superficial or substantial: Why care about microplastics in the Anthropocene? *Environ Sci Technol* **2018**, *52*, (6), 3336-3337.
20. Backhaus, T.; Wagner, M., Microplastics in the environment: Much ado about nothing? A debate. *peerJ Preprints* **2018**, *6*:e26507v6.
21. Maynard, A. D., Don't define nanomaterials. *Nature* **2011**, *475*, (7354), 31-31.
22. Stamm, H., Nanomaterials should be defined. *Nature* **2011**, *476*, (7361), 399-399.
23. Rauscher, H.; Roebben, G.; Sanfeliu, A. B.; Emons, H.; Gibson, N.; Koeber, R.; Linsinger, T.; Rasmussen, K.; Sintes, J. R.; Sokull-Klüttgen, B.; Stamm, H. *Towards a*

review of the EC Recommendation for a definition of the term “nanomaterial”, Part 3:
Scientific-technical evaluation of options to clarify the definition and to facilitate its
implementation; European Commission Joint Research Centre: 2015.

24. European Commission, Commission Recommendation of 18 October 2011 on the
definition of nanomaterial (2011/696/EU). In Official Journal of the European Union,
2011; p L 275/38.
25. Brennholt, N.; Heß, M.; Reifferscheid, G., Freshwater microplastics: Challenges for
regulation and management. In *Freshwater Microplastics*, Wagner, M.; Lambert, S., Eds.
2018; pp 239-272.
26. International Union of Pure and Applied Chemistry, *Compendium of polymer terminology
and nomenclature: IUPAC recommendations, 2008*. RSC Pub.: Cambridge, 2009; p 443.
27. Lechner, M. D.; Gehrke, K.; Nordmeier, E. H., *Makromolekulare Chemie*. Springer
Spektrum: Berlin, Heidelberg, 2014.
28. Ivleva, N. P.; Wiesheu, A. C.; Niessner, R., Microplastic in Aquatic Ecosystems. *Angew
Chem Int Ed Engl* **2017**, *56*, (7), 1720-1739.
29. Lambert, S.; Wagner, M., Environmental performance of bio-based and biodegradable
plastics: the road ahead. *Chem Soc Rev* **2017**, *46*, (22), 6855-6871.
30. Pfaendner, R., How will additives shape the future of plastics? *Polym Degrad Stabil*
2006, *91*, (9), 2249-2256.
31. Hahladakis, J. N.; Velis, C. A.; Weber, R.; Iacovidou, E.; Purnell, P., An overview of
chemical additives present in plastics: Migration, release, fate and environmental impact
during their use, disposal and recycling. *J Hazard Mater* **2018**, *344*, 179-199.
32. European Chemicals Agency, Guidance for monomers and polymers. In Guidance for
the implementation of REACH: Helsinki, 2012; p 26.
33. Lambourne, R.; Strivens, T. A., *Paint and surface coatings - theory and practice*.
Woodhead Publishing Ltd: Abington, 1999.
34. Verschoor, A.; Poorter, L. d.; Dröge, R.; Kuenen, J.; de Valk, E. *Emission of
microplastics and potential mitigation measures - Abrasive cleaning agents, paints and*

563 *tyre wear*, National Institute for Public Health and the Environment: Bilthoven, 2016; p
564 75.

565 35. MEPEX *Sources of microplastics-pollution to the marine environment*; Norwegian
566 Environment Agency: 2014; p 86.

567 36. Eunomia *Plastics in the marine environment*, Bristol, 2016; p 13.

568 37. MEPEX *Primary microplastic-pollution: Measures and reduction potentials in Norway*,
569 Norwegian Environment Agency: 2016; p 117.

570 38. Lassen, C.; Hansen, S. F.; Magnusson, K.; Norén, F.; Hartmann, N. I. B.; Jensen, P. R.;
571 Nielsen, T. G.; Brinch, A. *Microplastics - Occurrence, effects and sources of releases to*
572 *the environment in Denmark*; The Danish Environmental Protection Agency:
573 Copenhagen, 2015.

574 39. UNECE *Globally Harmonized System of Classification and Labelling of Chemicals*
575 *(GHS) - Fifth revised edition*; United Nations: New York and Geneva, 2013.

576 40. Rogovina, L. Z.; Vasil'ev, V. G.; Braudo, E. E., Definition of the concept of polymer gel.
577 *Polym Sci Ser C* **2008**, 50, (1), 85-92.

578 41. European Chemicals Agency, Guidance on information requirements and chemical
579 safety assessment, Part B: Hazard Assessment. In Guidance for the implementation of
580 REACH: Helsinki, 2010; p 19.

581 42. Besseling, E.; Quik, J. T. K.; Sun, M.; Koelmans, A. A., Fate of nano- and microplastic in
582 freshwater systems: A modeling study. *Environ Pollut* **2017**, 220, 540-548.

583 43. Huffer, T.; Praetorius, A.; Wagner, S.; von der Kammer, F.; Hofmann, T., Microplastic
584 exposure assessment in aquatic environments: Learning from similarities and
585 differences to engineered nanoparticles. *Environ Sci Technol* **2017**, 51, (5), 2499-2507.

586 44. Scherer, C.; Brennholt, N.; Reifferscheid, G.; Wagner, M., Feeding type and
587 development drive the ingestion of microplastics by freshwater invertebrates. *Sci Rep*
588 **2017**, 7, (1), 17006.

45. International Organization for Standardization Nanotechnologies - Vocabulary, Part 1: Core terms (ISO/TS 80004-1:2015). <https://www.iso.org/obp/ui/#iso:std:iso:ts:80004:-1:ed-2:v1:en> (19.09.2016),
46. Hidalgo-Ruz, V.; Gutow, L.; Thompson, R. C.; Thiel, M., Microplastics in the marine environment: a review of the methods used for identification and quantification. *Environ Sci Technol* **2012**, *46*, (6), 3060-75.
47. Zhang, K.; Xiong, X.; Hu, H.; Wu, C.; Bi, Y.; Wu, Y.; Zhou, B.; Lam, P. K.; Liu, J., Occurrence and characteristics of microplastic pollution in Xiangxi Bay of Three Gorges Reservoir, China. *Environ Sci Technol* **2017**, *51*, (7), 3794-3801.
48. Lusher, A. L.; Welden, N. A.; Sobral, P.; Cole, M., Sampling, isolating and identifying microplastics ingested by fish and invertebrates. *Anal Methods* **2017**, *9*, (9), 1346-1360.
49. MSFD Technical Subgroup on Marine Litter *Guidance on monitoring of marine litter in European seas - a guidance document within the common implementation strategy for the Marine Strategy Framework Directive*; European Commission, Joint Research Centre, Institute for Environment and Sustainability: Luxembourg, 2013; p 128.
50. Fendall, L. S.; Sewell, M. A., Contributing to marine pollution by washing your face: microplastics in facial cleansers. *Mar Pollut Bull* **2009**, *58*, (8), 1225-8.
51. Lei, K.; Qiao, F.; Liu, Q.; Wei, Z.; Qi, H.; Cui, S.; Yue, X.; Deng, Y.; An, L., Microplastics releasing from personal care and cosmetic products in China. *Mar Pollut Bull* **2017**, *123*, (1-2), 122-126.
52. Wardrop, P.; Shimeta, J.; Nugegoda, D.; Morrison, P. D.; Miranda, A.; Tang, M.; Clarke, B. O., Chemical Pollutants Sorbed to Ingested Microbeads from Personal Care Products Accumulate in Fish. *Environ Sci Technol* **2016**, *50*, (7), 4037-44.
53. Ory, N. C.; Sobral, P.; Ferreira, J. L.; Thiel, M., Amberstripe scad *Decapterus muroadsi* (Carangidae) fish ingest blue microplastics resembling their copepod prey along the coast of Rapa Nui (Easter Island) in the South Pacific subtropical gyre. *Sci Total Environ* **2017**, *586*, 430-437.

- 616 54. Lambert, S.; Wagner, M., Microplastics are contaminants of emerging concern in
617 freshwater environments: An overview. In *Freshwater Microplastics*, 2018; pp 1-23.
- 618 55. Mani, T.; Blarer, P.; Storck, F. R.; Pittroff, M.; Wernicke, T.; Burkhardt-Holm, P.,
619 Repeated detection of polystyrene microbeads in the lower Rhine River. *Environ Pollut*
620 **2018**, *245*, 634-641.
- 621 56. Browne, M. A.; Galloway, T.; Thompson, R., Microplastic - an emerging contaminant of
622 potential concern? *Integr Environ Assess Manag* **2007**, *3*, (4), 559-561.
- 623 57. Moore, C. J., Synthetic polymers in the marine environment: A rapidly increasing, long-
624 term threat. *Environ Res* **2008**, *108*, (2), 131-139.
- 625 58. Ryan, P. G.; Moore, C. J.; van Franeker, J. A.; Moloney, C. L., Monitoring the
626 abundance of plastic debris in the marine environment. *Philos Trans R Soc Lond B Biol*
627 *Sci* **2009**, *364*, (1526), 1999-2012.
- 628 59. Costa, M. F.; Ivar do Sul, J. A.; Silva-Cavalcanti, J. S.; Araujo, M. C.; Spengler, A.;
629 Tourinho, P. S., On the importance of size of plastic fragments and pellets on the
630 strandline: a snapshot of a Brazilian beach. *Environ Monit Assess* **2010**, *168*, (1-4), 299-
631 304.
- 632 60. Desforges, J. P.; Galbraith, M.; Dangerfield, N.; Ross, P. S., Widespread distribution of
633 microplastics in subsurface seawater in the NE Pacific Ocean. *Mar Pollut Bull* **2014**, *79*,
634 (1-2), 94-9.
- 635 61. Wagner, M.; Scherer, C.; Alvarez-Munoz, D.; Brennholt, N.; Bourrain, X.; Buchinger, S.;
636 Fries, E.; Grosbois, C.; Klasmeier, J.; Marti, T.; Rodriguez-Mozaz, S.; Urbatzka, R.;
637 Vethaak, A. D.; Winther-Nielsen, M.; Reifferscheid, G., Microplastics in freshwater
638 ecosystems: what we know and what we need to know. *Environ Sci Eur* **2014**, *26*, (1),
639 12.
- 640 62. Andrady, A. L., *Plastics and environmental sustainability*. Wiley: Hoboken, New Jersey,
641 2015; p 324.
- 642 63. Koelmans, A. A.; Kooi, M.; Law, K. L.; van Sebille, E., All is not lost: deriving a top-down
643 mass budget of plastic at sea. *Environ Res Lett* **2017**, *12*, (11).

644 64. EFSA Panel on Contaminants in the Food Chain, Statement on the presence of
645 microplastics and nanoplastics in food, with particular focus on seafood. *EFSA Journal*
646 **2016**, 14, (6), 30.

648 Table 1. Overview of the recommendations for a definition and classification of plastic debris.

| Criterion | Recommendation | Examples |
|---------------------------------|---|---|
| Ia: Chemical composition | | |
| ✓ Include | All synthetic polymers: <ul style="list-style-type: none"> ▪ Thermoplastics ▪ Thermosets ▪ Elastomers ▪ Inorganic/hybrid | All commodity plastics Polyurethanes, melamine Synthetic rubber Silicone |
| ✓ Include | Heavily modified natural polymers (semi-synthetic) | Vulcanized natural rubber, regenerated cellulose |
| × Exclude | Slightly modified natural polymers | Dyed natural fibers |
| Ib: Additives | | |
| ✓ Include | All polymers included in Ia disregarding their additive content | Plasticized PVC with >50 % additives |
| Ic: Copolymers | | |
| ✓ Include | All copolymers | ABS, EVA, SBR |
| Id: Composites | | |
| ✓ Include | All composites containing synthetic polymer as essential ingredient | Reinforced polyester and epoxy |
| ✓ Include | All surface coatings containing polymers as essential ingredient | Paints containing polyester, PUR, alkyd, acrylic, epoxy resin |
| ✓ Include | Tire wear (and road) particles | - |
| ? Open question | Is it necessary to define a minimum polymer content? | |
| II: Solid state | | |
| ✓ Include | All polymers with a T_m or $T_g > 20\text{ °C}$ | See examples in Ia |
| × Exclude | Polymer gels | PVA, PEG |
| ? Open question | Should wax-like polymers ($T_g < 20\text{ °C}$) be included? | |
| III: Solubility | | |
| ✓ Include | All polymers with a solubility $< 1\text{ mg L}^{-1}$ at 20 °C | See examples in Ia |
| IV: Size | | |
| | <ul style="list-style-type: none"> ▪ Nanoplastics: 1 to $< 1,000\text{ nm}$ ▪ Microplastics: 1 to $< 1,000\text{ }\mu\text{m}$ ▪ Mesoplastics: 1 to $< 10\text{ mm}$ ▪ Macroplastics: 1 cm and larger <p>The largest dimension of the object determines the category. Comprehensive reporting of dimensions is preferred (e.g., for fibers).</p> | |
| V: Shape and structure | | |
| | <p>Spheres: Every surface point has the same distance from the center</p> <p>Spheroid: Imperfect but approximate sphere</p> <p>Cylindrical pellet: Rod-shaped, cylindrical object</p> <p>Fragment: Particle with irregular shape</p> <p>Film: Planar, considerably smaller in one than in the other dimensions</p> <p>Fiber: Significantly longer in one than wide in two dimensions</p> <p>Additional information on the structure (e.g., porosity) can be included.</p> | |
| VI: Color | | |
| | Not crucial for a categorization but useful in a biological context (e.g., when color is a cue for ingestion). Use a standardized color palette. | |
| VII: Origin | | |
| | <p>Primary: Intentionally produced in a certain size</p> <p>Secondary: Formed by fragmentation in the environment or during use</p> <p>Origin should only be used if the primary origin can be established.</p> | |

Figures




Figure 1. Examples of differences in the categorization of plastic debris according to size as applied (and/or defined) in scientific literature and in institutional reports. It should be noted that this does not represent an exhaustive overview of all used size classes.




Figure 2. Proposed definition and categorization framework. Excl. = excluded, see Table 1 for details on criteria.